

Gulf Guard 601 Top Coat

Product Description

Gulf Guard 601 Top Coat is based on special synthetic resin high quality single component solvent based product. It is providing maximum protection for steel surfaces. It is distinguished by its quick drying; mechanical & chemical resistance.

Recommended Usage

To be used as a top coat for interior and exterior steel surfaces.

Technical Data

| | | | |
|---|--------------------------------------|---------|---------|
| Color | As per color card. | | |
| Finish | Smooth / Glossy, Semi Gloss or Matt. | | |
| Component | Single | | |
| Solid contents | 45 % ± 2 by volume | | |
| | Minimum | Maximum | Typical |
| Wet film thickness (microns) | 89 | 111 | 100 |
| Dry film thickness (microns) | 40 | 50 | 45 |
| Theoretical spreading rate (m ² /ltr.) | 11 | 9 | 10 |
| Viscosity | 8 - 12 poises at 25° C | | |
| Specific gravity | 1.15 ± 0.05 gm/cm ³ . | | |
| Drying time | Dry to touch (hours) | | 1 |
| | Dry to recoat (hours) | | 6 |
| Thinner / Cleaning | Falco Thinner 1050 | | |

Hint

Theoretical spreading rate is a value that depends on solid content and desired dry film thickness by the following equation:

$$\text{Theoretical spreading rate} = \frac{10 \times \text{solid content by volume}}{\text{DFT in microns}}$$

Application Data

Surface Preparation

The surface must be clean, dry and free from dust, oil, grease and any contaminations.

Tools

Brush, roller or spray.

Spray Data

Pressure at nozzle : 150 kg/cm² (2100 PSI)
 Nozzle tip (inches) : 0.018 - 0.021
 Spray Angle : 65 - 80°
 Filter : be sure that the filters are clean.

Application Method

Apply Two coats of **Gulf Guard 601 Top Coat** (top coat) by brush, roller and spray thinned with Thinner 1050 (10-15% by volume).

Recommended paint system:

- Gulf Guard 601 Primer 1 coat
- **Gulf Guard 601 top coat** 2 coats

Recommended paint system non ferrous surfaces:

- Falco Wash Primer 1 coat
- Gulf Guard 601 Primer 1 coat
- **Gulf Guard 601 top coat** 2 coats

Note: paint system may be varying according to the substrate.

Packing size

- 1 liter, 1 US gallon and 5 US gallons steel cans (for local).
- 1 liter, 1 US gallon, 18 liters steel cans (for export).

Storage

- The product should be stored in a dry, cool place and away from direct sun light.
- Cans should be well closed, classified according to the base and to be arranged by a maximum 3 plastic cans/row and 5 steel cans/row.

Health and safety

- Inhalation Risks:

Vapor or mist can cause headache, nausea & irritation of the nose throat & lungs.

- Skin & Eye Contact:

Use good personal hygiene practices while working with this material. Dry contaminated clothing before reuse. For eye contact, flush with fresh water for at least 15 minutes. If irritation persists, get medical attention.

- Skin Absorption : Not expected.

- Ingestion Health Risks:

It may be harmful or fatal if swallowed. ingestion may cause nausea, vomiting & diarrhea. Consult a physician.

- Health Hazards : Acute & chronic (not expected).

- Emergency & First Aid Procedures:

1. Dermal : Clean with soap & water.
2. Ingestion : Consult a physician.
3. Inhalation : Remove to fresh air.

Fire & Fire Fighting Data

| | |
|---------------------|---|
| Flash Point | : closed cup 28° C. |
| Flammable limits | : None. |
| Extinguishing media | : Foam, Alcohol Foam, CO2 and dry chemical. |

Physical / Chemical Characteristics

| | |
|---------------------|----------------------|
| Vapor Density | : Heavier than air. |
| Evaporation Rate | : Slower than other. |
| Solubility in Water | : Soluble. |
| Appearance/Odor | : Liquid, Mild Odor |

For more information please refer to the Material Safety Data Sheet.