

Gulf Guard M.I.O Top Coat

Product Description

Gulf Guard M.I.O Top Coat is a two pack primer based on a high molecular weight epoxy resin pigmented with micaceous iron oxide. Especially formulated to provide maximum water, abrasion, solvent and chemical resistant.

Recommended Usage

To be used as a primer for steel structure and pipe works.

Technical Data

Color	Grey.	Grey.		
Finish	Matt.	Matt.		
Solid contents	57 % ± 2 by vol	57 % ± 2 by volume.		
	Minimum	Maximum	Typical	
Wet film thickness (microns)	175	263	220	
Dry film thickness (microns)	100	150	125	
Theoretical spreading rate (m2/ltr.)	5.7	3.8	4.5	
Specific gravity	1.38 ± 0.05 gm.	1.38 ± 0.05 gm/cm ³		
Drying time	Dry to touch (hours)		2	
		Dry to recoat (hours)		
	Fully cured (day	Fully cured (days)		
Thinner / Cleaning	Falco Thinner 20	Falco Thinner 2050		
Mixing ratio	4 parts A (base)	4 parts A (base) : 1 part B (hardener)		
Pot life	4 Hrs. @ 25°C to	4 Hrs. @ 25°C to be less at higher temp.		

<u>Hint</u>

Theoretical spreading rate is a value that depends on solid content and desired dry film thickness by the following equation:

Theoretical spreading rate =

10 x solid content by volume

DFT in micron

Application Data

Surface Preparation

The surface must be clean, dry and free from dust, oil, grease and any contaminations.

Tools

Brush, roller or spray.

Spray Data

Pressure at nozzle : 150 kg/cm2 (2100 PSI)

Nozzle tip (inches) : 0.021 - 0.031Spray Angle : $40 - 80^{\circ}$

Filter : be sure that the filters are clean.

TDS 04-017 (Ver. 02) Page 1 of 2



Application Method

Apply Two coats of Gulf Guard M.I.O Top Coat by brush, roller or spray thinned with Thinner 2050 (10-15% by volume).

Recommended paint system full epoxy:

Gulf Guard M.I.O primer
 Gulf Guard M.I.O Top Coat
 2 coats

Note: paint system may be varying according to the substrate.

Packing size

- 1 liter, 1 US gallon and 5 US gallons steel cans (for local).
- 1 liter, 1 US gallon, 18 liters steel cans (for export).

Storage

- The product should be stored in a dry, cool place and away from direct sun light.
- Cans should be well closed, classified according to the base and to be arranged by a maximum 3 plastic cans/row and 5 steel cans/row.

Health and safety

Inhalation Risks:

Vapor or mist can cause headache, nausea & irritation of the nose throat & lungs.

• Skin & Eye Contact:

Use good personal hygiene practices while working with this material. Dry contaminated clothing before reuse. For eye contact, flush with fresh water for at least 15 minutes. If irritation persists, get medical attention.

- <u>Skin Absorption</u> : Not expected.
- Ingestion Health Risks:

It may be harmful or fatal if swallowed. ingestion may cause nausea, vomiting & diarrhea. Consult a physician.

- Health Hazards : Acute & chronic (not expected).
- Emergency & First Aid Procedures:

Dermal : Clean with soap & water.
 Ingestion : Consult a physician.
 Inhalation : Remove to fresh air.

Fire & Fire Fighting Data

Flash Point : closed cup 21° C.

Flammable limits : None.

Extinguishing media : Foam, Alcohol Foam, CO2 and dry chemical.

Physical / Chemical Characteristics

Vapor Density : Heavier than air. Evaporation Rate : Slower than other.

Solubility in Water : Soluble.

Appearance/Odor : Liquid, Mild Odor

For more information please refer to the Material Safety Data Sheet.

TDS 04-017 (Ver. 02) Page 2 of 2